

## SunCoat New Horizon Screen Emulsion YC4101 & YC4105

## SunCoat Screen Making Products

### 1. Description

SunCoat New Horizon is a dual sensitized (dual cure) screen emulsion capable of producing photo-stencils of an extremely high quality with a low surface tack. It should be used where high definition and resolution are required and is recommended for four colour process printing. SunCoat New Horizon may be used with UV curing, solvent based, plastisol and many water based inks. SunCoat New Horizon is a two-pack system and is available in pack sizes of 0.9kg (YC4101) and 4.5kg (YC4105).

### 2. Product Features\*

- Dual cure emulsion
- Low surface tack
- Highest quality stencils and excellent print definition
- Solvent, UV, plastisol and water resistant
- Ideal for four colour process stencils

\*Specific application performance data, where available can be provided by your Sun Chemical representative.

### 3. Product Suitability\*

#### 3.1 Applications

SunCoat New Horizon is a dual sensitized (dual cure) screen emulsion capable of producing photo-stencils of an extremely high quality. It should be used where high definition and resolution are required and is recommended for four colour process printing. SunCoat New Horizon may be used with UV curing, solvent based, plastisol and many water based inks.

### 4. General Handling

#### 4.1 Storage and Shelf Life

SunCoat New Horizon unsensitized emulsion should be stored in closed containers at temperatures between 5°C - 20°C and will have a minimum shelf life of 18 months but can remain usable for longer periods depending on storage conditions. Once sensitised, SunCoat New Horizon can be stored for approximately 4 to 6 weeks, if kept cool, preferably in a refrigerator.

#### 4.2 Light Sensitivity

SunCoat New Horizon emulsion is already light sensitive before the sensitiser is added and must therefore be handled in safe light conditions from opening.

For more specific handling advice refer to the Safety Data Sheet.



## 5. Application Conditions\*

### 5.1 Screen Preparation

All screens must be degreased prior to emulsion coating, either manually or in an automatic system. The use of SunCoat degreasing products is recommended.

### 5.2 Sensitising

Half fill the diazo sensitiser container with warm water, reseal and shake the bottle for a few moments to fully dissolve the diazo sensitiser powder. Add the entire contents of the sensitiser bottle to the emulsion and mix thoroughly with a non-metallic spatula. Allow 2 to 3 hours, or preferably overnight, for any air bubbles in the mixture to fully disperse.

### 5.3 Coating

SunCoat New Horizon emulsion may be used with all mesh grades. 2 coats on substrate side, 1 coat on squeegee side, or 2 coats on substrate side and 2 coats on squeegee side are recommended. When applying SunCoat New Horizon wet on wet, always coat the squeegee side last, so as to push the emulsion through the mesh onto the substrate side of the screen. SunCoat New Horizon Emulsion is fully suited for use with both automatic and hand coating techniques.

### 5.4 Drying

After coating, the screen should be dried in a horizontal position, squeegee side up in light safe and dust free conditions. Drying can be assisted with a fan heater but the temperature should not rise above 40°C. Once dried the pre-exposed screens may be stored for up to 2 weeks in cool, light safe, low humidity conditions.

### 5.5 Exposure

SunCoat New Horizon emulsion is intended for high quality work where accurate resolution is needed and therefore the use of dyed mesh is strongly recommended. Exposure time depends upon many variables such as mesh count and colour, thickness of emulsion film and intensity and distance of the light source.

The table below is a guide only and is based on a 2 + 1 emulsion coating on a 150 and 120 thread per cm, 34 micron thread diameter, dyed screen mesh.

| SunCoat New Horizon Exposure Time Guide |                         |                             |                               |
|---|-------------------------|-----------------------------|-------------------------------|
| Metal Halide Light Source Power (W)     | Mesh Grade (Threads/cm) | Distance Bulb To Screen (M) | Approximate Exposure Time (s) |
| 3500                                    | 120                     | 1.2                         | 300 to 350                    |
| 5000                                    | 150                     | 1.2                         | 75 to 90                      |

To achieve a more accurate exposure time, the use of an exposure calculator is strongly recommended.

### 5.6 Developing

After exposure, the squeegee side should be wetted with cold water, then the stencil completely washed out from the print side using a high pressure jet at a distance of approximately half a metre. Complete the process by gently rinsing the squeegee side to remove any emulsion residue. Dry the screen at a temperature not exceeding 45°C.

English Version 3  
May 2023  
PDS No. 959  
2/3



### 5.7 Reclaiming

SunCoat New Horizon emulsion may be easily removed. All traces of ink should be removed from the screen using a suitable screenwash before following the guidelines of the chosen stencil strip product. SunCoat stencil strip products are particularly recommended. SunCoat New Horizon emulsion may be reclaimed using manual techniques and automatic cleaning / stripping equipment.

\*Please refer to your local Sun Chemical representative for specific details.

## 6. End-use safety

### 6.1 Handling

SunCoat New Horizon emulsion should be used in accordance with normal standards of industrial hygiene. It is strongly recommended that gloves and goggles are worn during use and that good air ventilation is provided in usage areas. SunCoat New Horizon emulsion contains some irritant materials and the sensitiser is acidic, therefore contact with skin and eyes should be avoided.

Please refer to the information provided on product labels and relevant Safety Data Sheets.

## 7. Technical Assistance / Contacts

For further information, please contact your local Sun Chemical team.

Our Products are intended for sale to professional users. The information herein is general information designed to assist customers in determining the suitability of our products for their applications. All recommendations are made without guarantee, since the application and conditions of use are beyond our control. We recommend that customers satisfy themselves that each product meets their requirements in all respects before commencing a print run. There is no implied warranty of merchantability or fitness for purpose of the product or products described herein. In no event shall Sun Chemical be liable for damages of any nature arising out of the use or reliance upon this information. Modifications of the product for reasons of improvements might be made without further notice.

English Version 3  
May 2023  
PDS No. 959  
3/3

Registered Address: Sun Chemical Ltd, 3 High View Road, South Normanton, Derbyshire, DE55 2DT, UK. Tel: +44 1773 815 704

