

Product Data Sheet

Pad Printing Ink

SunChemical®
Coates Screen Inks

TP 260

Solvent Based Pad Printing Ink Range, 2-Component

APPLICATION

Pad printing inks for printing on metals, coated surfaces, duroplastics and special thermoplastics such as pre-treated polypropylene (PP) and polyethylene (HD-PE, LD-PE), PMMA ("acrylic glass"), polyamide (PA), polyacetal (POM), polyurethane (PU) and polyester (PES).

PROPERTIES

- Pad inks TP 260 are solvent based pad printing inks. They are processed as 2-component ink with hardener.
- Ink range TP 260 shows good printability. The inks dry chemical-physically with a high degree of cross-linkage and result in a glossy finish.
- TP 260 inks are suitable for a variety of applications, especially for technical/industrial applications requiring exceptionally high resistances.
- Cured prints exhibit very high mechanical resistances as well as very good chemical resistances against many organic solvents, thinned alkalis and acids, oils and grease.
- Due to the binders (epoxy resin) pad printing inks TP 260 are not suitable for outdoor applications.
- TP 260 inks are certified according to USP Medical Class VI. They can be used for printing onto medical devices.
- Note: Because of the variety of substrates, pre-tests are essential. It is also advised to check efficiency of possibly required pre-treatment of substrates (cleaning/degreasing, flame/corona/plasma treatment) or maybe even post-treatment (flame-drying).

COLOUR SHADES - OVERVIEW

- Mixing System: C-MIX 2000 12 colour shades for mixing of RAL, PMS and HKS colours.
- Opaque: Standard Colour shades with medium to good opacity.
Standard HD Highly opaque colour shades.
- Process Inks: „180“ colours 4 transparent colour shades according to ISO 2846-4.
- Special colour shades are available upon request.
- More information about available colour shades in the detailed tables in section Colour Shades.

CHOICE OF PIGMENTS AND LIGHT FASTNESS

Colour shades of TP 260 ink range contain pigments with a high light fastness. Light fastness and weather resistance will reduce if thinner layers are applied or if base colours are mixed with a high ratio of white or varnish. Due to the binders (epoxy resin) pad printing inks TP 260 are not weather resistant. They are not suitable for outdoor applications.

ADJUSTMENT FOR PAD PRINTING

- Pad printing inks TP 260 are not supplied in a ready-to-print adjustment.
- As this ink range is a 2-component system TP 260 inks have to be mixed with hardener at a specified ratio prior to processing.
- Thinner is added after addition of hardener.
- The mixed ink should be allowed to pre-react for approx. 15 minutes prior to processing (recommendation).
- Processing is then possible for a specified period of time (=pot life).

Hardener:

Pad printing inks TP 260 are mixed with **hardener TP 219**.

Hardener is added to TP 260 inks at a specified ratio:

Ink : Hardener = 2 : 1 (parts by weight).

Hardeners are sensitive to humidity. Therefore, containers always have to be tightly closed.

Pot life:

- Ink mixed with hardener may only be processed within a limited period of time (=pot life)
- **Pot life of TP 260 + hardener TP 219 is approx. 6 h (at 20°C).**
Higher temperatures will reduce pot life.
- We do not recommend processing the inks for longer than the pot life as adhesion and resistance properties will then continually deteriorate, even if the ink still seems to be liquid and processable.

THINNERS / RETARDERS

Depending on local conditions ink is adjusted to printing consistency by addition of 15 – 30 % by weight of thinner or retarder.

Generally, the thinner suitable for TP 260 inks is Additive A!

The additional products listed below should only be used if the required printing quality cannot be achieved using additive A (e.g. drying too slow or too fast).

For adjustment of pad inks TP 260, the following products are available:

| | | |
|------------------|--|---|
| Thinner: | <input type="radio"/> Additive C | Extremely quick thinner, good solving power |
| | <input type="radio"/> VD 40 | Quick thinner, very strong solving power |
| | <input type="radio"/> Additive B | Quick thinner, good solving power |
| | <input checked="" type="radio"/> Additive A | Standard thinner |
| | <input type="radio"/> Additive U | Standard thinner, free of cyclohexanone |
| | <input type="radio"/> VD 60 | Slow thinner |
| Retarder: | <input type="radio"/> TPD | Very slow retarder |

■= Preferred ○= If required

Note: **For printing with thick and thin steel clichés sensitive to corrosion**

| | |
|-------------------------------------|---|
| <input type="radio"/> Additive A/00 | Standard thinner with anti-corrosion additive |
| <input type="radio"/> Additive B/00 | Quick thinner with anti-corrosion additive |

Depending on printing conditions, the products listed above can be mixed into the inks individually or as mixtures. Please note that depending on evaporation rate of the thinner/retarder used drying times may be longer.

Thinner/retarder should be mixed into the ink thoroughly using a mixer or agitator. In addition, inks should be stirred well prior to each processing to obtain a homogeneous dispersion of all ingredients.

ADDITIONAL AUXILIARY AGENTS

| Application | Product | Addition in % by weight | Additional Information |
|--------------------|-------------------|-------------------------|---------------------------------|
| Antistatic paste | LAB-N 111420 | Max. 10% | Possibly slightly reduced gloss |
| Retarder paste | LAB-N 111420/VP | Max. 10% | Possibly slightly reduced gloss |
| Viscosity increase | Thickening powder | Max. 5% | Stir with mixer |
| Matting | Matting powder | Max. 5% | Stir with mixer |
| Flow agent | VM 1 | 1 - 5% | Do not overdose! |

OVERPRINTING

Generally, it is not necessary to overprint TP 260 inks with varnish. However, overprinting to achieve an enhanced protection of ink layers is possible with TP 260/E50. Overprinting should be carried out within <12 hours.

BRONZE COLOURS, MIXING OF BRONZE INKS

Bronze colours 75/AB to 79/AB and metal gloss colours 75/MG to 79/MG are available upon request. Printers can mix bronzes themselves using bronze pastes B 75, B 76, B 77 and B 79 as well as bronze powder B 78-POWDER. For examples of colour shades please refer to our Bronze Colour Card.

These “B” bronze pastes and “B” bronze powder are mixed with bronze binder TP 260/B or varnish TP 260/E50 prior to processing.

Mixing ratios in parts by weight:

Gold bronze paste/powder to TP 260/B or TP 260/E50 = 1 : 3 - 4

Silver bronze paste to TP 260/B or TP 260/E50 = 1 : 4 - 5

Contrary to AB and MG bronze colours, B bronzes are prone to oxidation (Exception B 78-POWDER). Therefore, they should be overprinted, e.g. with TP 260/E50.

B 78-POWDER does not tend to oxidation. The pale copper shade will not darken with time. Colour of inks mixed with B 78-POWDER is similar to colour 78/AB as shown on our “bronze colour card”.

Note: When overprinting bronze colours (B/ AB/ MG) with varnish or other colour shades it is essential to carry out pre-tests to check intermediate adhesion of the ink layers (fingernail test, tape test).

Overprinting should be carried out within <12 hours.

DRYING / HARDENER REACTION

Mixture of TP 260 ink/hardener is a chemically-reactive system with a high degree of cross-linkage and physical pre-drying.

- Ink dries physically by evaporation of solvents.
- Then the ink film cures by chemical cross-linkage reaction.
- **Drying and reaction temperature of hardener TP 219 must be at least 15°C!**

Drying

Drying times below are only approximate as drying properties depend on various factors:

- Type and amount of thinners/retarders used.
- Thickness of printed ink layer (single print, multi-layer print).
- Drying temperature.

Drying time is approx. 2 minutes at room temperature (20 – 25°). Drying time with heat application (e.g. hot air fan) and air circulation is about 30 - 40 seconds.

Complete drying may take up to several hours, also depending on the substrate.

Hardener Reaction

Basically, the special resistance properties of the printed ink film are only achieved after complete drying followed by chemical cross linkage reaction between ink and hardener. This cross linkage reaction depends on time and temperature. Until fully cured the minimum temperatures should not fall below 15°C. In addition, avoid high humidity.

Cross-linkage reaction will be much quicker using higher temperatures.

The following are guide values only:

| Temperature | Time approx. | Condition of ink | Additional information |
|------------------|----------------|---------------------------------|--|
| <15°C air drying | | Hardener TP 219 does not react! | Ink film will not achieve any resistance |
| 20°C air drying | 20 min. | “touch-dry” | No resistance yet |
| | <12 h | Still good overprintability | No resistance yet |
| | >72 h | High degree of cross-linkage | High resistances achieved |
| | >5 days | Maximum degree of cross-linkage | Maximum resistances achieved |
| 80°C oven curing | approx. 5 min. | Dry enough for overprinting | No resistance yet |
| | 60 min. | High degree of cross-linkage | High resistance values achieved |
| 140° oven curing | 30 min. | Maximum degree of cross-linkage | Maximum resistance values achieved |

Resistance Tests

Resistances should not be checked before the ink has fully cured/cross-linked:

Drying with 20°C/5 days; 80°C/>60 minutes* 140°C/30 minutes*

*After oven curing allow a cooling time (room temperature 20°C) of at least 1h.

CLICHÉ

All commercial types of clichés (polymer, thin and thick steel, ceramic) are suitable for processing TP 260 inks.

Note: Standard shades 17, 50, 51 and 65-HD cannot be used for closed ink systems with a magnet holder as they contain pigments with iron oxide content.

CLEANING

The longer inks dry on clichés, pots and tools the harder will be their removal due to the chemical cross-linkage reaction. Therefore, always remove ink residues as soon as possible using our universal cleaning agents URS, URS 3 or thinner VD 40.

PACK SIZE

Pad printing inks TP 260 are delivered in 1 litre containers. Other pack sizes are available upon request.

SHELF LIFE

In closed original containers, TP 260 inks generally have a shelf life of 5 years from date of production. Hardener TP 219 has a shelf life of 14 months from date of production, also in closed original containers.

For exact date of expiry, please refer to the label.

SAFETY DATA SHEETS

Read safety data sheet prior to processing

Safety data sheets comply with Regulation (EC) No. 1907/2006 (REACH), Appendix II.

CLASSIFICATION AND LABELLING

Hazard classification and labelling comply with Regulation (EC) No. 1272/2008 (CLP/GHS).

CONFORMITY

Coates Screen Inks GmbH does not use any of the substances or mixtures for the production of printing inks, which are banned according to the EUPIA (European Association of the Printing Inks Industry) exclusion policy.

Further compliance confirmations are available upon request.

ADDITIONAL INFORMATION ABOUT OUR PRODUCTS

Product data sheets: Auxiliary Agents for Pad Printing HM

Brochures: Pad Printing Inks

Internet: Various technical articles are available for download on www.coates.de, section "SN-Online"; e.g. "Processing of 2-component Inks"

FOR COLOUR RANGES, PLEASE REFER TO NEXT PAGE.

COLOUR SHADES

| C-MIX 2000 BASE COLOUR SHADES | | | | | |
|---|-----------------|----------------------------|----------------------------|-----------------|--------------|
| Mixing system for matching of PMS, HKS, RAL colours (on white substrates) Start formulations available in data base „Formula Management C-MIX 2000“ According to colour card C-MIX 2000 | | | | | |
| primrose | TP 260/Y30 | red | TP 260/R50 | green | TP 260/G50 |
| golden yellow | TP 260/Y50 | magenta | TP 260/M50 | black | TP 260/N50 |
| orange | TP 260/O50 | violet | TP 260/V50 | white | TP 260/W50 |
| scarlet | TP 260/R20 | blue | TP 260/B50 | varnish | TP 260/E50 |
| STANDARD (medium opacity) | | | | | |
| According to colour card STANDARD 2 for pad printing inks or TP 218/ TP 260... Availability of further standard shades upon request | | | | | |
| citric yellow | TP 260/10-NT | carmin red | TP 260/22-NT | light green | TP 260/40-NT |
| medium yellow | TP 260/11-NT | pink | TP 260/25-NT | fir green | TP 260/41-NT |
| dark yellow | TP 260/12-NT | light blue | TP 260/30-NT | brilliant green | TP 260/42-NT |
| orange | TP 260/15-NT | medium blue | TP 260/31-NT | dark brown | TP 260/51-NT |
| ochre yellow | TP 260/17-NT | ultra marine | TP 260/32-NT | white | TP 260/60-NT |
| light red | TP 260/20-NT | dark blue | TP 260/33-NT | black | TP 260/65-NT |
| bright red | TP 260/21-NT | violet | TP 260/37-NT | | |
| STANDARD Colour Range HD (high opacity) | | | | | |
| According to colour card STANDARD HD for pad printing inks Availability of further standard HD shades upon request | | | | | |
| citric yellow, highly opaque | TP 260/10-HD-NT | violet, highly opaque | TP 260/37-HD-NT | | |
| medium yellow, highly opaque | TP 260/11-HD-NT | light green, highly opaque | TP 260/40-HD-NT | | |
| bright red, highly opaque | TP 260/21-HD-NT | white, highly opaque | TP 260/60-HD-NT | | |
| carmin red, highly opaque | TP 260/22-HD-NT | black, highly opaque | TP 260/65-HD-NT | | |
| light blue, highly opaque | TP 260/30-HD-NT | | | | |
| SPECIAL PRODUCTS: Special Colour Shades, Varnishes, Pastes | | | | | |
| Information about availability upon request | | | | | |
| white, matt | TP 260/60-MT | matt paste | TP 260/MP | | |
| black, matt | TP 260/65-MT-NT | bronze binder | TP 260/B | | |
| black, low-grade PAH | TP 260/68-NT | overprint varnish, matt | TP 260/70-MT | | |
| 4 COLOUR PROCESS INKS (CMYK) | | | | | |
| According to colour card STANDARD 2 for pad printing inks or TP 218/ TP 260... | | | | | |
| process yellow | TP 260/180-NT | process black | TP 260/65-NT | | |
| process magenta | TP 260/181-NT | transparent paste | TP 260/TP | | |
| process cyan | TP 260/182-NT | | | | |
| AB – BRONZE INKS and MG – METAL GLOSS INKS | | | | | |
| According to Bronze Colour Card | | | | | |
| AB Bronze Inks | | | MG Metal Gloss Inks | | |
| Upon request | | | Upon request | | |

Matching of PMS, RAL, NCS colours and special shades upon request.

The statements in our product and safety data sheets are based on our present experiences, however they are no assurance of product properties and do not justify a contractual legal relationship. We provide these details to inform customers about our products and their possible applications. However, on account of various factors influencing processing of our products it is absolutely essential to carry out printing trials under local production conditions. Choice of individual ink types and their suitability for the intended application is the sole and entire responsibility of the user. We do not assume any liability for any problems of technical or process-related nature. Any liability shall be limited to the value of the goods delivered by us and processed by the user.

All former product data sheets are no longer valid.

April 2020 - Version B2

Coates Screen Inks GmbH
Wiederholdplatz 1 90451 Nürnberg
Tel.: 0911 6422 0 Fax: 0911 6422 200
<http://www.coates.de>