

# Solvent-Based Screen Printing Inks

Ink Ranges	A	CP	CX	HG	J	LAB-N 331213	PF	PK/PK-Jet	PP	TL (Fluorescent Ink)	XL	TZ	YN	ZE 1690	Z/PVC	TP 253/L	Z	Z/DD	Z/GL	ZGM	ZM	ZMN	
Addition of Hardener	☐	☐	☐	☐	☐	☐	☐	☐	☐	☐	☐	☐	☐	☐	☐	☐	☐	☐	☐	☐	☐	☐	
Drying	⊗	▲	▲	▲	▲	▲	▲	▲	▲	▲	▲	▲	▲	▲	▲	▲	▲	▲	▲	▲	▲	▲	▲
PVC plasticized		●	●	●			●	●	●					●									
PVC rigid	●	●	●	●			●	●	●			●		●									
Polystyrene (PS)		●	●	●	○		●		●		●	●											
ABS, SAN		●		●			●		●		●	●		●		●			●	●	●		
Polycarbonate (PC)		●	●	●	●		●		●	●	●	●		●		●	●			●	●	●	
Acrylic glass (PMMA)	●	●	●	●	●		●		●	●	●	●		●		●			●	●	●		
Polyester film For membrane switch overlays				●	●				○														
Polyester (PET)				○	○	●						●				●	●		●				
PET-G		○		○						●													
Polyamide (PA) Pre-treatment recommended						●					2	2				●			●		●		
with pre-treatment Polypropylene (PP)						●		●				2		2		●	●		●	●	●		
Polyethylen (PE)																							
without pre-treatment Polypropylen (PP)								●															
Polyacetal (POM)												2				●			●	●	○		
Polyurethane (PUR)				○	○						2	2							●				
Silikon rubber															●								
TPE/TPU, Rubber, Synthetic leather											2	2											
Leather, Textiles											2	2											
Duroplastics	●				●							2				●	●	●	●				
Glass																			●	●			
Metals	○				●							2				●	●	●	●	●	●	●	
Coated Surfaces	●			●	●	●									●	●			●			●	
Wood	●											●											
Paper, Paperboard, Cardboard		●	●	●		●		●															

- = preferred for the application
- ② = processing with hardener required
- = suitable for the application
- ② = processing with hardener required
- = potentially suitable

- ☑ = **Does not contain:** aromatics, cyclohexanone, butyl glycolate, PAH, Solvent Naphtha
- ☐ = 1 - component ink
- ☐ = processing as 1 - and 2 - component ink
- = 2 - component ink
- ▲ = air-drying
- ① = oven - curing at 140°C/20 Min
- ② = oven - curing at 160°C/20 Min
- ⊗ = Drying by oxidation

The information given above is no guarantee for the suitability of screen printing inks for individual substrates. The intention of this chart is to help printers choose suitable screen printing inks. Pre-tests are always essential. This information is based on our present experiences 06/2019

**Coates Screen Inks GmbH**  
 Nuremberg Screen and Pad Printing Inks  
 Wiederholdplatz 1 · 90451 Nuremberg  
 Tel: +49 911 64 22-0  
 Fax: +49 911 64 22 200  
 info.coates@sunchemical.com  
 www.coates.de